Technical data sheet

# STEICO*multi tape black*

**High performance tape with special surface**



**High performance black tape with surface that can be plastered, for internal and external use**

- Solvent-free
- Can be processed from -10 °C, temperature resistant between -40° and +100°C
- High UV and ageing resistance
- High moisture resistance/ rainproof
- With split release paper for the simple formation of e.g. corner bonds

## Application area



- Joint and connection bonding of STEICO wood fibre boards in combination with STEICO*multi primer*
- Joint and connection bonding with STEICO*universal black*
- Connection bonding for STEICO*fix* and STEICO*tri* sub-window sills

## Technical data

| | |
|---|---|
| Temperature resistance | -40 / +100 °C |
| Processing temperature | ≥ -10 (substrate must be dry and free of ice) °C |
| Minimum roof pitch | 10 ° |
| Adhesive | Acrylic dispersion, solvent-free |
| Adhesive backing | UV-stabilized special fleece, adhesive on one side |
| Colour | Black without print |
| Thickness (without release paper) | ~ 0,6 mm |
| UV resistance | 6 (before applying the façade cladding) months |
| Peeling strength | complies with DIN 4108-1 |
| Peel strength after ageing | complies with DIN 4108-11 |

## Forms of delivery

**Roll mit slashed back**

| Length [mm] | Width [mm] | Release liner perforation [mm] | Number/pack. [pcs.] |
|---|---|---|---|
| 25000 | 70 | 20/50 | 8 |
| 25000 | 140 | 50/20/70 | 4 |

Technical data sheet

# STEICO*multi tape black*

**High performance tape with special surface**

## Weight and packing

**Roll mit slashed back**

| Length [mm] | Width [mm] | Weight/m²[kg] | Weight/pcs. [kg] | Weight/pack. [kg] | Packaging/pack. Paper/cardboard (approx.) [kg] |
|---|---|---|---|---|---|
| 25000 | 70 | 0.65 | 0.8 | 7.50 | 0.80 |
| 25000 | 140 | 0.65 | 1.6 | 7.50 | 1.20 |

## Notes

### Storage

- Store in a cool and dry place at +5 to +25 °C
- Protect from heat, cold and UV radiation

### Ingredients

- Acrylic dispersion (solvent-free), UV-stabilized special fleece

### Disposal

- dispose with normal construction waste, observe applicable legal guidelines

### Cutting

- Sharp knife or other suitable cutting tool

## Installation

### Application in the STEICO membrane system

- Substrates must be stable, dry and free of dust and grease.
- Align STEICO*multi tape black*, remove the release paper step by step, and rub the tape down firmly.
- Slit release paper makes it easier to bond corners, as liners can be removed in turn as required.
- Apply STEICO*multi tape black* without tension or creases.
- If tensile forces occur, the substrate must also be mechanically fastened.
- Bonds must not be in standing water. Bonding in sauna and swimming pool construction is also not permitted.

### Installation on STEICO wood fibre boards

- Pre-treat STEICO wood fibre boards in the bonding area with STEICO*multi primer*.
- After sufficient flash-off time (if primer is transparent), apply STEICO*multi tape black*, remove release paper and rub on.
- The bonding area per butt joint side must be at least 50 mm.
- To improve adhesion, additional pressing with a paint roller or roofing roller is recommended
- Once the adhesive tape has been applied, it can be plastered over

Technical data sheet

# STEICO*multi tape black*

High performance tape with special surface

## Certificates and quality management

## Caption

### other abbreviations

**pal.** Pallet
**T&G** Tongue and Groove
**pac.** Packaging
**approx.** Approximately
**EUR** Europe

## Compliance

**Responsible for content**

STEICO SE
Otto-Lilienthal-Ring 30
85622 Feldkirchen
Germany
Web: www.steico.com
Mail: info@steico.com

**Version: 2**
**Date: 2026-07-03**

**Liability disclaimer**

The contents of this document have been compiled with the utmost care. However, applicable standards and regulations can change. STEICO accepts no liability for the accuracy, completeness and current applicability of the standards and regulations presented. Always check compliance with standards and regulations and the suitability of our products for the specific intended use, and make any necessary adjustments during installation.

STEICO accepts no responsibility for the completeness, accuracy or quality of information provided by third parties.

**Regional document validity: EU***

***Additional Validity Information**

The contents of this document have been prepared in consideration of European product standards and provide a general overview of component structures, construction methods, and installation. Local applicable regulations have not been considered.

The most recent version of this document applies. This version can be found at:
www.steico.com/tds_steicomulti_tapeblack_eur_en